

RV SPRAY-UP MER B1 MULTI-END ROVING


Reliable spray-up processing



Spray-up MER B1 Roving represents a multi-end roving product for chopper gun operations.


- ✔ Multi-end gun roving reinforcement using Advantex® glass fiber, which combines the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass
- ✔ Advantex® glass roving has a sizing system designed to provide performance for spray-up applications

Product Benefits



Wet-Out Performance

Designed to provide competitive performance for spray-up applications where value-based performance in wet-out speed is preferred, accepted performance in various types of composite parts



Value-Based Option

Spray-up product offering that is a cost-effective solution which leverages competitive choppability, dispersion, and restrains static development

Application

RV Spray-up MER B1 Roving can be used in a variety of spray-up applications including boats, truck caps, heavy-truck body parts, bathtubs, showers, spas, tanks, pools, etc.

Technical Characteristics

LINEAR WEIGHT OF ROVING (TEX)	YIELD	LOSS ON IGNITION (%) ISO 1887:1995
2400	207	0.85

Availability

PRODUCT	DOFF Ø (MM)	PALLET DIMENSIONS LxW (CM)	LAYERS PER PALLET	DOFFS PER LAYER	TOTAL NUMBER OF DOFFS	CREEL-PAK®	PALLETS APPROX. FIBERGLASS
						NUMBER OF ENDS	WEIGHT* (KG/LB)
RV Spray-Up MER B1 2E/2400	281	114 X 114	3	16	48	2	907/2000

Packaging & Labeling

Each Spray-Up MER B1 2E/2400 doff is protected by a tack-wrap polythene film and identified by an individual label; please do not remove film during use. Creel-Pak® is standard product offering

Each doff has a self-adhesive identification label, showing the product reference and the production date.

Each pallet has five identification labels detailing the product reference, pallet net and gross weights, production date and pallet production code.

Storage

Unless otherwise specified, it is recommended that glass fiber products be stored in a cool, dry area. Recommended long-term storage conditions are temperatures between 10°C and 35°C and relative humidity between 35% and 85%. While temporary deviations may occur during storage or transportation, product performance can be confirmed through routine verification testing if exposure outside these conditions has occurred for an extended period. Glass fiber products should remain in their original packaging until the point of use. To help prevent condensation, keep product in its original, unopened packaging and allow it to naturally acclimate to the workshop temperature for at least 24 hours before opening or use. Packaging is not waterproof and should be protected from weather and other sources of moisture. Although fluctuations may occur during transportation, handling, and temporary storage, products should be maintained within the recommended storage ranges after receipt to help preserve product performance. A defined shelf life has not been established for the product when stored under recommended conditions. However, retesting is recommended after two years from the date of manufacture to help ensure optimum performance.

MAKE
MORE
POSSIBLE™

US & Canada
2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user’s process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.