

ME1510

MULTI-END ROVING

Higher performance for
transportation and beyond




ME1510 multi-end roving represents a compelling solution for structural applications requiring high mechanical properties. This multi-end roving product increases physical properties – enabling vehicle light weighting, increased fuel efficiency and lower CO₂ emissions.

-  Compatible with epoxy and phenolic resins.
-  Produced with patented Advantex® corrosion resistant E-CR glass.


Product Benefits

- 

Excellent Processing
 - Due to excellent wettability in epoxy and phenolic matrices, very high glass content is achievable, enabling excellent processing while compounding.
- 

Outstanding Mechanical Properties
 - Superior strength and flexural modulus enable light weighting in vehicles to increase fuel efficiency, lower CO₂ emissions and increase range in electric vehicles.
- 

Enhanced Service Life
 - Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.
- 

Fire Resistant
 - Compatible with phenolic resins used in fire resistance applications such as electric vehicles.
- 

No Odor
 - Epoxy resin system meets low odor requirements in vehicles.

Application

ME1510 is designed to provide optimal performance in Sheet Molding Compound (SMC) applications including: automotive structural parts, electric vehicles, and critical industrial applications that require higher mechanical properties such as oil and gas exploration.

Technical Characteristics

LINEAR WEIGHT OF ROVING	LOSS ON IGNITION (%) ISO 1887:1995	MOISTURE CONTENT (%) ISO 3344:1997
2400 and 4800 TEX 207 and 103 Yield	0.7	≤ 0.10

Availability

Each pallet can be packaged in bulk or Creel-Pak™ packaging format. Pallets are stretch-wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak™ packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

PRODUCT	DOFF CHARACTERISTICS			
	DIAMETER (mm)		HEIGHT (mm)	NOMINAL WEIGHT (kg)
	Internal	External		
ME1510 2400 and 4800 TEX	46	285 to 290	254	20.5

Packaging & Labeling

Each bobbin is protected by a plastic film (Tack-Pak®). Please do not remove film during use. Creel-Pak® packaging is available upon request.

Each bobbin has a self-adhesive identification label, showing the product reference and the production date. Each pallet has at least one identification label detailing the product reference, pallet net and gross weights, production date and pallet production code.

The packaging system is designed to allow short term stacking of two pallets. When stacking two-high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.

Storage

Unless otherwise specified, it is recommended that glass fiber products be stored in a cool, dry area. Recommended long-term storage conditions are temperatures between 10°C and 35°C and relative humidity between 35% and 85%. While temporary deviations may occur during storage or transportation, product performance can be confirmed through routine verification testing if exposure outside these conditions has occurred for an extended period. Glass fiber products should remain in their original packaging until the point of use. To help prevent condensation, keep product in its original, unopened packaging and allow it to naturally acclimate to the workshop temperature for at least 24 hours before opening or use. Packaging is not waterproof and should be protected from weather and other sources of moisture. Although fluctuations may occur during transportation, handling, and temporary storage, products should be maintained within the recommended storage ranges after receipt to help preserve product performance. A defined shelf life has not been established for the product when stored under recommended conditions. However, retesting is recommended after two years from the date of manufacture to help ensure optimum performance.

MAKE
MORE
POSSIBLE™

US & Canada
2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

South America
Av. Brasil, 2567
Rio Claro/SP, Brasil
13500-600
0800 707 3312

China
Room 301C+304,
1188 Minsheng Road,
Pudong, Shanghai
201705, China
+86 21 8010 3596

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.