

ST2070 SINGLE-END ROVING

Optimal noise
reduction, less cost



Type 30® ST2070 single-end roving is specifically designed for use in the Silentex® Exhaust filling process. The product is designed to minimize process interruptions and ensure efficiency in filling automotive mufflers with continuous fibers. This creates a muffler that is highly effective in reducing sound with increased resistance to blowout.

✓ Robust solution to meet demanding acoustic requirements, support increasing engine temperatures, and lower overall cost of silencers as well as reduced weight, volume, and back pressure.

✓ Produced with patented Advantex® corrosion resistant E-CR glass.

FOR DEMANDING NOISE CONTROL SOLUTIONS USING SILENTEX®

Product Benefits



Enhanced Service Life & Durability

- Advantex® glass provides longer service life with a high temperature composition specifically engineered for use in the Silentex® process, which minimizes process interruptions and ensures overall product efficiency.
- Fibers remain continuous and resist blowout with five times the strength of basalt wool and twice the strength of E-glass under the most corrosive conditions.
- Glass annealing point ≥ 720 °C (according to ASTM C336).
- Based on the available data and experience, it is recommended to use ST2070 at a maximum continuous glass temperature of ~740 °C.



Excellent Processing

- Smooth run-out from lower drag across contact points produces less fuzz, resulting in smoother parts, less clean-up, and improved machine efficiencies.



Consistent Performance

- Narrow and consistent fiber diameter distribution for reliable sound absorption for reduced fill density compared to basalt preforms or needle felt.

Application

ST2070 is designed for use in the manufacture of cost-effective automotive muffler systems with optimal durability and acoustic performance.



Availability & Packaging

PRODUCT	AVE. FILAMENT DIAMETER (µm): ISO 1888	LINEAR DENSITY (tex): ISO 1889	LOSS ON IGNITION (%): ISO 1887	MOISTURE (%): ISO 3344	MANUFACTURING REGION
ST2070	24	7000±560; 4800±400	0.34 (max 0.5)	<0.2	Americas, Europe, Asia Pacific

MANUFACTURING REGION	PRODUCT (tex)	PACKAGING	PALLET WIDTH (MM/IN)	PALLET LENGTH (MM/IN)	PALLET HEIGHT (MM/IN)	PALLET NET WEIGHT (KG)
Americas (U.S.)	ST2070 4800	Creel-Pak®	1150.62/45.3	1150.62/45.3	1219.2/48	~1215
Americas (U.S.)	ST2070 7000	Creel-Pak® 1end	1150.62/45.3	1150.62/45.3	1219.2/48	~1095
Americas (U.S.)	ST2070 7000	Creel-Pak®	1150.62/45.3	1150.62/45.3	914.4/36	~864
Europe (France)	ST2070 7000	Creel-Pak® 1end or 2end and Bulk	800	1200	1000	750–760
Asia Pacific (China)	ST2070 7000	Creel-Pak® 1end and Bulk	1150	1150	1000	~900
Asia Pacific (China)	ST2070 7000	Creel-Pak® 1end and Bulk	900	1150	1000	~675
Asia Pacific (India)	ST2070 4800	Creel-Pak® 1end and Bulk	1030	1030	1000	950–1100
Asia Pacific (India)	ST3000 4800	CTC boxes	1030	1030	500	500–550
Asia Pacific (India)	ST2070 4800	Single Ero Bulk Pack	1030	1030	1000	950–1100
Americas (Brazil)	ST2000 4800	Creel-Pak® 1end and Bulk	970	129	1100	1000–1100
Asia Pacific (South Korea)	ST1000 4800	Creel-Pak®	100	1100	1000	~850

Each pallet can be packaged in bulk or Creel-Pak® packaging format. Pallets are stretch wrapped for load stability and for protection during transport. All individual packages are wrapped with Tack-Pak® packaging to aid package run-out and transfer. More information is available in the Customer Acceptance Standards.

Labeling

Each individual package is labeled with information including: product name, tex/yield, producing plant, and production date.

Storage

Unless otherwise specified, it is recommended that glass fiber products be stored in a cool, dry area. Recommended long-term storage conditions are temperatures between 10°C and 35°C and relative humidity between 35% and 85%. While temporary deviations may occur during storage or transportation, product performance can be confirmed through routine verification testing if exposure outside these conditions has occurred for an extended period. Glass fiber products should remain in their original packaging until the point of use. To help prevent condensation, keep product in its original, unopened packaging and allow it to naturally acclimate to the workshop temperature for at least 24 hours before opening or use. Packaging is not waterproof and should be protected from weather and other sources of moisture. Although fluctuations may occur during transportation, handling, and temporary storage, products should be maintained within the recommended storage ranges after receipt to help preserve product performance. A defined shelf life has not been established for the product when stored under recommended conditions. However, retesting is recommended after three years from the date of manufacture to help ensure optimum performance.

MAKE
MORE
POSSIBLE™

US & Canada
2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

Europe (France)
767 Quai Des Allobroges
Chambery
Rhone-Alpes 73000, France
+33 4 79 75 55 52

India (Mumbai)
7th Floor, Alpha Building,
Hiranandani Gardens
Powai, Mumbai - 400076
+91 22 6668 1700

China
Room 301C+304,
1188 Minsheng Road,
Pudong, Shanghai
201705, China
+86 21 8010 3596

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user’s process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024022. ST2070 Product Data Sheet. October 2026. English. © 2026 OCF - Original Composites & Fiberglass. All Rights Reserved.