

CEM-FIL® 62

Efficient ductile performance



Cem-FIL® 62 is an integral strand glass fiber used to enhance the performance of drymix and GRC components manufactured in premixing processes.

✓ Produced with Cem-FIL® AR-glass, an alkali-resistant glass specifically designed for concrete reinforcement and lives up to a 50-plus-year reputation.

✓ Available in different strand diameters to optimize the fiber network

FOR DRYMIX OR PREMIX GRC APPLICATIONS

Product Benefits



Performance

- Improved ductility
- Excellent performance to dosage ratio due to the high fiber count
- High modulus for enhanced crack control
- Alkali-resistant glass*



Processing

- Friendly to automated dispensing
- Quick homogeneous dispersion
- Enables early demolding
- Safe and easy to handle
- Compatible with self-leveling systems



Aesthetics

- Ideal for use with complicated profiles
- Excellent reproduction of detail
- Makes durable, attractive GRC elements
- Superior finishability
- No risk of rust stains

Application

Cem-FIL® 62 is used in a variety of production processes with a sizing system optimized for performance and strand integrity during blending with dry material. Suited for pre-bagged mixes of repair and top screed mortars. Also suitable for standard GRC components consolidated by vibration or self-leveling admixtures.



Technical Characteristics

FIBER LENGTH	FILAMENT DIAMETER	TEX (g/km)	LOSS ON IGNITION (%) (ISO 1887:1995)	MOISTURE (%) (ISO 3344:1997)
6–12 mm/¼"–½"	13 µm	45	2.25	0.50 max
6–12–18 mm/¼"–½"–¾"	14 µm	82	1.75	

- Electrical Conductivity: Very low
 - Specific Gravity: 2.68 g/cm³
 - Material: Alkali-Resistant Glass*
 - Softening Point: 860°C/1 580°F
- Chemical Resistance: Very high
 - Modulus of Elasticity: 72 GPa–10x10⁶ psi
 - Tensile Strength of Input: >1 000 MPa – 145 ksi

*Our fibers are manufactured with high zirconia content in compliance with ASTM C1666 and EN 15422 and under the recommendations of PCI and GRCA.

Dosage

For drymix mortars and top screeds, recommended dosage is between 0.5 and 2%, or about 10–40 kg/m³ (17–68 lb/yd³). For premix GRC, the recommended dosage is from 1.5 to 3.0% by weight or about 30–60 kg/m³ (50–100 lb/yd³).

Packaging & Storage

Cem-FIL® 62 chopped strands are packed in plastic bags (5 kg) or carton boxes (15–22 kg). Cem-FIL® 62 chopped strands should be stored away from heat and moisture, and in their original packaging. Optimum conditions are temperatures between 15 °C and 35 °C and humidity between 35% and 65%. If the product is stored at lower temperatures, it is advisable to condition it in the workshop for at least 24 hours before use to prevent condensation.

Quality Standards

- Cem-FIL® 62 fibers are manufactured under a quality management system approved to ISO 9001.
- Cem-FIL® fibers are not classified as dangerous by the Regulation 1272/2008/EC. For information, please refer to our Safe Use Instruction Sheet.
- CE marking and Declaration of Performance as fibers for use in concrete and mortar through European Technical Assessment ETA 17/0169.
- Verified Environmental Product Declaration according to ISO 14025 and EN 15804:2019 available upon request.

MAKE
MORE
POSSIBLE™

US & Canada
2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

Europe (France)
767 Quai Des Allobroges
Chambery
Rhône-Alpes 73000, France
+33 4 79 75 55 52

China
Room 301C+304,
1188 Minsheng Road,
Pudong, Shanghai
201705, China
+86 21 8010 3596

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024896. Cem-FIL® 62 Product Data Sheet. July 2026. English. © 2026 OCF - Original Composites & Fiberglass. All Rights Reserved.