

ULTRASPAR®

High-performing spar caps



Ultraspar® combines the performance of WindStrand® 3000 with the consistency of the pultrusion process, allowing efficient, cost-effective blade design and production. High-performing glass-pultruded profiles enable lighter, longer blades, reducing the cost of wind energy.

✓ Produced with H-Glass, the high-modulus glass specifically designed for wind blades.

✓ Ultraspar® is pultruded with epoxy resin and is compatible with infusion in epoxy resin systems. Contact us regarding compatibility with other resin systems.

FOR EFFICIENT WIND BLADE PRODUCTION

Product Benefits



Proven Performance

- 60 GPa laminate 0° tensile modulus (at 70% FVF — Fiber Volume Fraction) — true performance to enable longer, lighter blades.
- Balances increased FVF to maintain strong fatigue performance.



Consistency And Productivity

- Pultrusion delivers consistent glass content for reliable performance and eliminates on-site spar cap infusion for improved productivity.
- Low porosity enables mechanical stability and quality consistency.
- Double-sided PA66 peel ply cover with easy peel-off provides an ideal contact surface for excellent bonding properties.

Application

Ultraspar® is a high-performance pultruded profile custom designed for wind blade spar caps. Ultraspar® enables blade designers to optimize the weight and maximize the length and strength of wind blades.



Properties

CHARACTERISTIC*	TEST METHOD	STRENGTH MEAN (MPa)	MODULUS MEAN (GPa)
0° Tensile**	ISO 527-5B	1,350	60
0° Compression**	ISO 527-5B	1,250	60
90° Tensile	ISO 527-5	50	15
90° Compression	ISO 14126	140	15
V-Notched Rail Shear	ASTM D7078	55	5
Fatigue (Tension-Tension)	ISO 13003	M value = 8.5	

* Typical FVF at 70%
** The sample piece is milled into a 2 mm thick rectangular coupon for testing
DATA SOURCE –Above typical data from OCF GL-certified lab and third-party lab

Availability & Packaging

This product is currently available in China. Please contact your representative for information in your region.

Ultraspar® is a custom-designed product requiring the profile dimensions of the specific design for a blade. Adequate time is needed for die preparation to properly produce the product.

Ultraspar® has coiled inner diameters of at least 1,500 mm and outer diameters up to 2,300 mm.

Storage

Glass fiber products should be stored in a dry area and remain in their original packaging until use. Products should be protected from the weather and other sources of water.

MAKE
MORE
POSSIBLE™

US & Canada
2790 Columbus Road
Building 70
Granville, Ohio, USA 43023
+1 866 2GET GLAS

Europe (France)
767 Quai Des Allobroges
Chambery
Rhone-Alpes 73000, France
+33 4 79 75 55 52

This information and data contained herein is offered solely as a guide in the selection of product. We do not guarantee its applicability to the user’s process or assume any responsibility or liability arising out of its use or performance. The physical and chemical properties of this product represent typical, average values obtained in accordance with stated test methods and are subject to normal manufacturing variations. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10024707. Ultraspar® Product Data Sheet. July 2026. English. © 2026 OCF - Original Composites & Fiberglass. All Rights Reserved.